

Technical Information Sheet

RubberCover Water Based Bonding Adhesive

Packaging	Part Number
2.5 l pail	W56RAC7200
5 l pail	W56RAC7201
10 l pail	W56RAC7202

Description

The Elevate™ RubberCover Water Based Bonding Adhesive is used only for wet-mating Elevate RubberCover EPDM membranes onto acceptable wooden substrates.

Application

RubberCover Water Based Bonding Adhesive can be applied in following Elevate system(s): RubberCover™ EPDM.

Preparation

Surfaces that will receive the RubberCover Water Based Bonding Adhesive must be clean, smooth, dry, and free of sharp edges, loose and foreign materials, oil, grease, and other contaminants. The mating surface shall be cleaned with a brush or clean rag. If the product has been exposed to temperatures lower than 15°C for a prolonged period, restore the adhesive to room temperature (15°-25°C) before use. Stir the adhesive thoroughly (to achieve a uniform mix with no sediment on the bottom and no marbling evident) before and during use.

Method of Application

RubberCover Water Based Bonding Adhesive will be mated, while still wet, directly over plywood or OSB substrates (only types that are not treated against water absorption). Apply Water Based Bonding Adhesive at a rate of approx. 350 gr/m² over plywood or OSB with a paint roller, taking care to completely cover the plywood or OSB substrate evenly to avoid globs and puddles of adhesive. The EPDM membrane shall be mated immediately after the bonding adhesive is applied by rolling the membrane in place over the plywood or OSB. To ensure proper adhesion, compress the bonded portion of the sheet to the substrate with a stiff push broom or heavy roller.

Caution: The EPDM membrane should not be exposed to any wind stresses for 48 hours after mating. Moreover, the adhesive layer cannot be subjected to freezing temperatures for a minimum of 48 hours after the mating of EPDM to the substrate.

Coverage

Coverage rate needs to be between 2.5 and 3 m² per liter.

Some surfaces are more uneven and porous and will result in lower coverage rates, while smoother substrates are less porous and will, therefore, result in higher rates.

Characteristics

Technical	
• Base	Acrylic dispersion
• Color	White
• Solids	min. 55%
• Viscosity	36000-44000 cp
• Specific gravity	1.02

Storage

Store in original unopened containers at moderate temperatures (15°C-25°C) in a dry, well-ventilated area. Protect from direct sunlight. Do not allow product to freeze. If necessary, use an insulated box to maintain the product at moderate temperatures during transport to the job site, before and during application. This will ensure the appropriate viscosity, efficiency, and performance of the adhesive.

Shelf Life

12 months can be expected if stored in the conditions mentioned above. Verify the production date on each pail. Subzero temperatures will make the product unusable. Shelf life information is only a recommendation and not a fact of life. The real expiration date highly depends on the history of storage and handling of the accessories. Once opened, use within 48 hours.

Disposal

Make sure that the pail is empty before disposal. Adhesive cannot be disposed in drains. Dispose content and/or pail in accordance with national regulations.

Precautions

For professional use only. Use only in well-ventilated areas. Thinning is not allowed. Do not contaminate with foreign materials; avoid contact with water-sensitive materials. Do not expose to excess heat, as it may lead to excess pressure. Do not walk through spilled material. Avoid prolonged inhalation and skin/eye contact. In case of contact, immediately flush skin/eyes with running water for at least 20 minutes. Wash skin with soap and water. Refer to Safety Data Sheets for additional information.

Note:

This document is meant only to highlight Elevate products and specifications based on latest knowledge and experience and is subject to change without notice. Above mentioned values are based on tested samples and may vary within applicable tolerances. For latest and complete product and detail information, please refer to the technical information posted on www.holcimelevate.com. Holcim Solutions and Products EMEA BV ("Holcim") takes responsibility for furnishing quality materials which meet Holcim's published product specifications. As neither Holcim itself nor its representatives practice architecture, Holcim offers no opinion on and expressly disclaims any responsibility for the soundness of any structure on which its products may be applied. The selection of the appropriate product and its correct application is the responsibility of the customer and not of Holcim. No Holcim Representative is authorized to vary this disclaimer.